


## Product Specification – AmeriGrid EL160-660

Tensar International Corporation reserves the right to change its product specifications at any time. It is the responsibility of the person specifying the use of this product and of the purchaser to ensure that product specifications relied upon for design or procurement purposes are current and that the product is suitable for its intended use in each instance.

Tensar TriAx<sup>®</sup> Geogrid

### General

1. The geogrid is manufactured from a punched polypropylene sheet, which is then oriented in three substantially equilateral directions so that the resulting ribs shall have a high degree of molecular orientation, which continues at least in part through the mass of the integral node.
2. The properties contributing to the performance of a mechanically stabilized layer include the following:



Index Properties	Longitudinal	Diagonal	Transverse	General
▪ Rib pitch <sup>(2)</sup> , mm (in)	40 (1.60)	40 (1.60)	-	
▪ Mid-rib depth <sup>(2)</sup> , mm (in)	-	1.6 (0.06)	1.4 (0.06)	
▪ Mid-rib width <sup>(2)</sup> , mm (in)	-	1.0 (0.04)	1.2 (0.05)	
▪ Rib shape				Rectangular
▪ Aperture shape				Triangular

### Structural Integrity

▪ Junction efficiency <sup>(3)</sup> , %				93
▪ Radial stiffness at low strain <sup>(4)</sup> , kN/m @ 0.5% strain (lb/ft @ 0.5% strain)				300 (20,580)

### Durability

▪ Resistance to chemical degradation <sup>(5)</sup>				100%
▪ Resistance to ultra-violet light and weathering <sup>(6)</sup>				70%

### Dimensions and Delivery

The TX geogrid shall be delivered to the jobsite in roll form with each roll individually identified and nominally measuring 6 feet in width and 60 feet in length.

### Notes

1. Unless indicated otherwise, values shown are minimum average roll values determined in accordance with ASTM D4759-02. Brief descriptions of test procedures are given in the following notes.
2. Nominal dimensions.
3. Load transfer capability determined in accordance with ASTM D6637-10 and ASTM D7737-11 and expressed as a percentage of ultimate tensile strength.
4. Radial stiffness is determined from tensile stiffness measured in any in-plane axis from testing in accordance with ASTM D6637-10.
5. Resistance to loss of load capacity or structural integrity when subjected to chemically aggressive environments in accordance with EPA 9090 immersion testing.
6. Resistance to loss of load capacity or structural integrity when subjected to 500 hours of ultraviolet light and aggressive weathering in accordance with ASTM D4355-05.

**Tensar International Corporation**  
 2500 Northwinds Pkwy.  
 Atlanta, Georgia 30009  
 Phone: 800-TENSAR-1  
[www.tensarcorp.com](http://www.tensarcorp.com)

This specification supersedes any and all prior specifications for the product designated above and is not applicable to any product shipped prior to January 31, 2014. Tensar and TriAx are trademarks of Tensar International Corporation or its affiliates in the US and many other countries. TriAx geogrid and the use thereof are protected by U.S. Patent No. 7,001,112. Patents or patent applications also exist in other countries. Final determination of the suitability of the above-mentioned information or product for the use contemplated, and its manner of use are the sole responsibility of the user. Tensar International Corporation disclaims any and all express, implied or statutory warranties, including but not limited to, any warranty of merchantability or fitness for a particular purpose regarding this product or the Company's other products, technologies or services. The information contained herein does not constitute engineering advice.