


Product Specification - TriAx® TX130S Geogrid¹

Tensor International Corporation reserves the right to change its product specifications at any time. It is the responsibility of the person specifying the use of this product and of the purchaser to ensure that product specifications relied upon for design or procurement purposes are current and that the product is suitable for its intended use in each instance.

General

1. The geogrid is manufactured from a punched polypropylene sheet, which is then oriented in three substantially equilateral directions so that the resulting ribs shall have a high degree of molecular orientation, which continues at least in part through the mass of the integral node.
2. The properties contributing to the performance of a mechanically stabilized layer include the following:

Tensor TriAx® Geogrid



Index Properties	Longitudinal	Diagonal	General
▪ Rib pitch ⁽²⁾ , mm (in)	33 (1.30)	33 (1.30)	
▪ Rib shape			Rectangular
▪ Aperture shape			Triangular

Structural Integrity

▪ Junction efficiency ⁽³⁾ , %			93
▪ Isotropic Stiffness Ratio ⁽⁴⁾			0.6
▪ Radial stiffness at low strain ⁽⁵⁾ , kN/m @ 0.5% strain (lb/ft @ 0.5% strain)			200 (13,708)

Durability

▪ Resistance to chemical degradation ⁽⁶⁾			100%
▪ Resistance to ultra-violet light and weathering ⁽⁷⁾			70%

Dimensions and Delivery

The TX geogrid shall be delivered to the jobsite in roll form with each roll individually identified and nominally measuring 3.0 meters (9.8 feet) and/or 4.0 meters (13.1feet) in width and 75 meters (246 feet) in length.

Notes

1. Unless indicated otherwise, values shown are minimum average roll values determined in accordance with ASTM D4759-02. Brief descriptions of test procedures are given in the following notes.
2. Nominal dimensions.
3. Load transfer capability determined in accordance with ASTM D6637-10 and ASTM D7737-11 and expressed as a percentage of ultimate tensile strength.
4. The ratio between the minimum and maximum observed values of radial stiffness at 0.5% strain, measured on rib and midway between rib directions.
5. Radial stiffness is determined from tensile stiffness measured in any in-plane axis from testing in accordance with ASTM D6637-10.
6. Resistance to loss of load capacity or structural integrity when subjected to chemically aggressive environments in accordance with EPA 9090 immersion testing.
7. Resistance to loss of load capacity or structural integrity when subjected to 500 hours of ultraviolet light and aggressive weathering in accordance with ASTM D4355-05.


Product Specification - TriAx® TX140 Geogrid

Tensor International Corporation reserves the right to change its product specifications at any time. It is the responsibility of the person specifying the use of this product and of the purchaser to ensure that product specifications relied upon for design or procurement purposes are current and that the product is suitable for its intended use in each instance.

General

- The geogrid is manufactured from a punched polypropylene sheet, which is then oriented in three substantially equilateral directions so that the resulting ribs shall have a high degree of molecular orientation, which continues at least in part through the mass of the integral node.
- The properties contributing to the performance of a mechanically stabilized layer include the following:

Tensor TriAx® Geogrid



Index Properties	Longitudinal	Diagonal	Transverse	General
▪ Rib pitch ⁽²⁾ , mm (in)	40 (1.60)	40 (1.60)	-	
▪ Mid-rib depth ⁽²⁾ , mm (in)	-	1.2 (0.05)	1.2 (0.05)	
▪ Mid-rib width ⁽²⁾ , mm (in)	-	1.1 (0.04)	1.1 (0.04)	
▪ Rib shape				Rectangular
▪ Aperture shape				Triangular

Structural Integrity

▪ Junction efficiency ⁽³⁾ , %				93
▪ Isotropic Stiffness Ratio ⁽⁴⁾				0.6
▪ Radial stiffness at low strain ⁽⁵⁾ , kN/m @ 0.5% strain (lb/ft @ 0.5% strain)				225 (15,430)

Durability

▪ Resistance to chemical degradation ⁽⁶⁾				100%
▪ Resistance to ultra-violet light and weathering ⁽⁷⁾				70%

Dimensions and Delivery

The TX geogrid shall be delivered to the jobsite in roll form with each roll individually identified. Rolls are shipped with nominal measurements: 3.0 meters (9.8 feet) in width by 75 meters (246 feet) in length, 4.0 meters (13.1 feet) in width by 75 meters (246 feet) in length, and 4.87 meters (16 feet) in width by 100 meters (328 feet) in length.

Notes

- Unless indicated otherwise, values shown are minimum average roll values determined in accordance with ASTM D4759-02. Brief descriptions of test procedures are given in the following notes.
- Nominal dimensions.
- Load transfer capability determined in accordance with ASTM D6637-10 and ASTM D7737-11 and expressed as a percentage of ultimate tensile strength.
- The ratio between the minimum and maximum observed values of radial stiffness at 0.5% strain, measured on rib and midway between rib directions.
- Radial stiffness is determined from tensile stiffness measured in any in-plane axis from testing in accordance with ASTM D6637-10.
- Resistance to loss of load capacity or structural integrity when subjected to chemically aggressive environments in accordance with EPA 9090 immersion testing.
- Resistance to loss of load capacity or structural integrity when subjected to 500 hours of ultraviolet light and aggressive weathering in accordance with ASTM D4355-05.


Product Specification - TriAx® TX150L Geogrid¹

Tensor International Corporation reserves the right to change its product specifications at any time. It is the responsibility of the person specifying the use of this product and of the purchaser to ensure that product specifications relied upon for design or procurement purposes are current and that the product is suitable for its intended use in each instance.

General

1. The geogrid is manufactured from a punched polypropylene sheet, which is then oriented in three substantially equilateral directions so that the resulting ribs shall have a high degree of molecular orientation, which continues at least in part through the mass of the integral node.
2. The properties contributing to the performance of a mechanically stabilized layer include the following:

Tensor TriAx® Geogrid



Index Properties	Longitudinal	Diagonal	General
<ul style="list-style-type: none"> ▪ Rib pitch⁽²⁾, mm (in) ▪ Rib shape ▪ Aperture shape 	57 (2.24)	57 (2.24)	Rectangular Triangular

Structural Integrity

<ul style="list-style-type: none"> ▪ Junction efficiency⁽³⁾, % ▪ Isotropic Stiffness Ratio⁽⁴⁾ ▪ Overall Flexural Rigidity⁽⁵⁾, mg-cm ▪ Radial stiffness at low strain⁽⁶⁾, kN/m @ 0.5% strain (lb/ft @ 0.5% strain) 			93 0.6 750,000 325 (22,270)
---	--	--	---

Durability

<ul style="list-style-type: none"> ▪ Resistance to chemical degradation⁽⁷⁾ ▪ Resistance to ultra-violet light and weathering⁽⁸⁾ 			100% 70%
---	--	--	-------------

Dimensions and Delivery

The TX geogrid shall be delivered to the jobsite in roll form with each roll individually identified and nominally measuring 4.0 meters (13.1feet) in width and 75 meters (246 feet) in length.


Notes

1. Unless indicated otherwise, values shown are minimum average roll values determined in accordance with ASTM D4759-02. Brief descriptions of test procedures are given in the following notes.
2. Nominal dimensions.
3. Load transfer capability determined in accordance with ASTM D6637-10 and ASTM D7737-11 and expressed as a percentage of ultimate tensile strength.
4. The ratio between the minimum and maximum observed values of radial stiffness at 0.5% strain, measured on rib and midway between rib directions.
5. Determined in accordance with ASTM D7748/D7748M-14.
6. Radial stiffness is determined from tensile stiffness measured in any in-plane axis from testing in accordance with ASTM D6637-10.
7. Resistance to loss of load capacity or structural integrity when subjected to chemically aggressive environments in accordance with EPA 9090 immersion testing.
8. Resistance to loss of load capacity or structural integrity when subjected to 500 hours of ultraviolet light and aggressive weathering in accordance with ASTM D4355-05.

Product Specification - TriAx® TX160 Geogrid

Tensor International Corporation reserves the right to change its product specifications at any time. It is the responsibility of the person specifying the use of this product and of the purchaser to ensure that product specifications relied upon for design or procurement purposes are current and that the product is suitable for its intended use in each instance.

Tensor TriAx® Geogrid



General

1. The geogrid is manufactured from a punched polypropylene sheet, which is then oriented in three substantially equilateral directions so that the resulting ribs shall have a high degree of molecular orientation, which continues at least in part through the mass of the integral node.
2. The properties contributing to the performance of a mechanically stabilized layer include the following:

Index Properties	Longitudinal	Diagonal	Transverse	General
▪ Rib pitch ⁽²⁾ , mm (in)	40 (1.60)	40 (1.60)	-	
▪ Mid-rib depth ⁽²⁾ , mm (in)	-	1.6 (0.06)	1.4 (0.06)	
▪ Mid-rib width ⁽²⁾ , mm (in)	-	1.0 (0.04)	1.2 (0.05)	
▪ Rib shape				Rectangular
▪ Aperture shape				Triangular
Structural Integrity				
▪ Junction efficiency ⁽³⁾ , %				93
▪ Isotropic Stiffness Ratio ⁽⁴⁾				0.6
▪ Radial stiffness at low strain ⁽⁵⁾ , kN/m @ 0.5% strain (lb/ft @ 0.5% strain)				300 (20,580)
Durability				
▪ Resistance to chemical degradation ⁽⁶⁾				100%
▪ Resistance to ultra-violet light and weathering ⁽⁷⁾				70%

Dimensions and Delivery

The TX geogrid shall be delivered to the jobsite in roll form with each roll individually identified. Rolls are shipped with nominal measurements: 3.0 meters (9.8 feet) in width by 75 meters (246 feet) in length, 4.0 meters (13.1 feet) in width by 75 meters (246 feet) in length, and 4.87 meters (16 feet) in width by 100 meters (328 feet) in length.

Notes

1. Unless indicated otherwise, values shown are minimum average roll values determined in accordance with ASTM D4759-02. Brief descriptions of test procedures are given in the following notes.
2. Nominal dimensions.
3. Load transfer capability determined in accordance with ASTM D6637-10 and ASTM D7737-11 and expressed as a percentage of ultimate tensile strength.
4. The ratio between the minimum and maximum observed values of radial stiffness at 0.5% strain, measured on rib and midway between rib directions.
5. Radial stiffness is determined from tensile stiffness measured in any in-plane axis from testing in accordance with ASTM D6637-10.
6. Resistance to loss of load capacity or structural integrity when subjected to chemically aggressive environments in accordance with EPA 9090 immersion testing.
7. Resistance to loss of load capacity or structural integrity when subjected to 500 hours of ultraviolet light and aggressive weathering in accordance with ASTM D4355-05.


Product Specification - TriAx® TX5 Geogrid

Tensor International Corporation reserves the right to change its product specifications at any time. It is the responsibility of the person specifying the use of this product and of the purchaser to ensure that product specifications relied upon for design or procurement purposes are current and that the product is suitable for its intended use in each instance.

General

1. The geogrid is manufactured from a punched polypropylene sheet, which is then oriented in three substantially equilateral directions so that the resulting ribs shall have a high degree of molecular orientation, which continues at least in part through the mass of the integral node.
2. The properties contributing to the performance of a mechanically stabilized layer include the following:

Tensor TriAx® Geogrid



Index Properties	Longitudinal	Diagonal	Transverse	General
▪ Rib pitch ⁽¹⁾ , mm (in)	40 (1.60)	40 (1.60)	-	
▪ Mid-rib depth ⁽¹⁾ , mm (in)	-	1.3 (0.05)	1.2 (0.05)	
▪ Mid-rib width ⁽¹⁾ , mm (in)	-	0.9 (0.04)	1.2 (0.05)	
▪ Rib shape				Rectangular
▪ Aperture shape				Triangular

Dimensions and Delivery

The TX geogrid shall be delivered to the jobsite in roll form with each roll individually identified. Rolls are shipped with nominal measurements: 3.0 meters (9.8 feet) in width by 75 meters (246 feet) in length, 4.0 meters (13.1 feet) in width by 75 meters (246 feet) in length, and 4.87 meters (16 feet) in width by 100 meters (328 feet) in length.

Notes

1. Nominal dimensions.


Product Specification - TriAx® TX7 Geogrid

Tensor International Corporation reserves the right to change its product specifications at any time. It is the responsibility of the person specifying the use of this product and of the purchaser to ensure that product specifications relied upon for design or procurement purposes are current and that the product is suitable for its intended use in each instance.

General

1. The geogrid is manufactured from a punched polypropylene sheet, which is then oriented in three substantially equilateral directions so that the resulting ribs shall have a high degree of molecular orientation, which continues at least in part through the mass of the integral node.
2. The properties contributing to the performance of a mechanically stabilized layer include the following:

Tensor TriAx® Geogrid



Index Properties	Longitudinal	Diagonal	Transverse	General
▪ Rib pitch ⁽¹⁾ , mm (in)	40 (1.60)	40 (1.60)	-	
▪ Mid-rib depth ⁽¹⁾ , mm (in)	-	2.0 (0.08)	1.6 (0.06)	
▪ Mid-rib width ⁽¹⁾ , mm (in)	-	1.0 (0.04)	1.3 (0.05)	
▪ Rib shape				Rectangular
▪ Aperture shape				Triangular

Dimensions and Delivery

The TX geogrid shall be delivered to the jobsite in roll form with each roll individually identified. Rolls are shipped with nominal measurements: 3.0 meters (9.8 feet) in width by 75 meters (246 feet) in length, 4.0 meters (13.1 feet) in width by 75 meters (246 feet) in length, and 4.87 meters (16 feet) in width by 100 meters (328 feet) in length.

Notes

1. Nominal dimensions.

Tensor International Corporation
2500 Northwinds Pkwy.
Atlanta, Georgia 30009
Phone: 800-TENSAR-1
www.tensorcorp.com

This specification supersedes any and all prior specifications for the product designated above and is not applicable to any product shipped prior to February 1, 2012. Tensor and TriAx are trademarks of Tensor International Corporation or its affiliates in the US and many other countries. TriAx® geogrid and the use thereof are protected by U.S. Patent No. 7,001,112. Patents or patent applications also exist in other countries. Final determination of the suitability of the above-mentioned information or product for the use contemplated, and its manner of use are the sole responsibility of the user. Tensor International Corporation disclaims any and all express, implied or statutory warranties, including but not limited to, any warranty of merchantability or fitness for a particular purpose regarding this product or the Company's other products, technologies or services. The information contained herein does not constitute engineering advice.


Product Specification - TriAx® TX8 Geogrid

Tensor International Corporation reserves the right to change its product specifications at any time. It is the responsibility of the person specifying the use of this product and of the purchaser to ensure that product specifications relied upon for design or procurement purposes are current and that the product is suitable for its intended use in each instance.

General

1. The geogrid is manufactured from a punched polypropylene sheet, which is then oriented in three substantially equilateral directions so that the resulting ribs shall have a high degree of molecular orientation, which continues at least in part through the mass of the integral node.
2. The properties contributing to the performance of a mechanically stabilized layer include the following:

Tensor TriAx® Geogrid



Index Properties	Longitudinal	Diagonal	Transverse	General
▪ Rib pitch ⁽¹⁾ , mm (in)	33 (1.30)	33 (1.30)	-	
▪ Mid-rib depth ⁽¹⁾ , mm (in)	-	1.6 (0.06)	1.2 (0.05)	
▪ Mid-rib width ⁽¹⁾ , mm (in)	-	0.4 (0.02)	0.7 (0.03)	
▪ Rib shape				Rectangular
▪ Aperture shape				Triangular

Structural Integrity

- | | |
|---|-----------------|
| ▪ Radial stiffness at low strain ⁽²⁾ , kN/m @ 0.5% strain
(lb/ft @ 0.5% strain) | 225
(15,400) |
|---|-----------------|

Dimensions and Delivery

The TX geogrid shall be delivered to the jobsite in roll form with each roll individually identified and nominally measuring 4.0 meters (13.1 feet) in width and 100 meters (328 feet) in length.

Notes

1. Nominal dimensions.
2. Radial stiffness is determined from tensile stiffness measured in any in-plane axis from testing in accordance with ASTM D6637.